



FISE TEHNICE PIGMENTI ANORGANICI

TIPUL PIGMENTULUI	ABSORPTIA IN APA (g/100g)	DENSIT. IN MASA (g/cm3)	COTINUT Fe2O3 (%)	CONTINUT SOL IN APA (%)	MARIMEA PARTIC. (µm)
OXID ROSUDE FIER - R01	35	0,7-1,1	96	4,0	0,09
OXID ROSU DE FIER - R02	31	0,7-1,1	96	4,0	0,12
OXID ROSU DE FIER - R03	28	0,7-1,1	96	4,0	0,17
OXID GALBEN DE FIER - 920	80	0,3-0,5	85	4,0	0,1x0,6
OXID MARON DE FIER - 663	32	0,8-1,2	94	4,0	0,1x0,6
OXID NEGRU DE FIER - 330	34	0,8-1,2	90	4,0	0,15
OXID ORANGE DE FIER 960	55	0,4-0,6	89	4,0	0,1-06
OXID VERDE DE CROM	13	1,0-1,3	98,5-99,5 Cr2O3	4,0	0,30

Cod Fiscal: RO 11683464, Nr. Inreg. Reg. Com: J23/346/2004

ING Bank Brancoveanu
Unicredit Tiriac Bank - Berceni
BRD – GSG Agentia Berceni:

RO58 INGB 0001 0081 9132 8910
RO68 BACX 0000 0045 7046 1001
RO37 BRDE 441S V480 0129 4410

Capital social : 3.000.000 Lei

